

TEL (478) 552 – 3951
FAX (478) 552 – 4131

EG-44

Typical Properties Sheet

G. E. Brightness

% Minimum 81.0

Particle Size

Finer than 2 Microns, % Minimum
Slurry and Spray Dried 88.0
Airfloat 85.0

Screen Residue Retained

325 Mesh, % Maximum .30

pH

Slurry as Shipped 6.5 - 7.5
Spray Dried @ 20% Solids 6.5 - 8.0
Airfloat @ 20% Solids 3.5 - 5.5

Moisture

Spray Dried , Bulk and Bags, % Maximum 1.5
Slurry, % Solids 69.0 - 71.0

EG-44 is a Fine Particle Size East Georgia Filler Clay.

Sales are made with the understanding that purchasers will determine the suitability of products for their particular purposes and Thiele makes no warranty for a particular purpose. No warranty of merchantability, nor other warranty, express or implied, is made. Similarly, Thiele Kaolin Company cannot assume responsibility for risks or liabilities, direct, indirect, or consequential, which may result from the use of its products. Likewise, no liability is assumed for any claimed patent infringement occurring by reason of any method of use of the customer.