

TEL (478) 552 – 3951
FAX (478) 552 – 4131

KAOBRITE

Product Specification Sheet

G. E. Brightness

% , Spray Dried	85.5 - 86.5
% , Slurry	85.5 - 87.0

Particle Size

Finer than 2 Microns, %	80 - 86
-------------------------	---------

Brookfield Viscosity

No. 1 Spindle, 20 rpm Typical @ 70% Solids, cP	300
---	-----

Screen Residue Retained

325 Mesh, % Maximum	.010
---------------------	------

pH

Slurry as Shipped or Spray Dried @ 20% Solids	6.5 - 7.5
--	-----------

Moisture

Spray Dried, Bulk and Bags, % Maximum	1.5
Slurry, % Solids	69.0 - 71.0

KAOBRITE is a NO. 2 Middle Georgia Coating Clay.

Sales are made with the understanding that purchasers will determine the suitability of products for their particular purposes and Thiele makes no warranty for a particular purpose. No warranty of merchantability, nor other warranty, express or implied, is made. Similarly, Thiele Kaolin Company cannot assume responsibility for risks or liabilities, direct, indirect, or consequential, which may result from the use of its products. Likewise, no liability is assumed for any claimed patent infringement occurring by reason of any method of use of the customer.