

Thiele Kaolin Company
P.O. Box 1056
Sandersville, GA 31082

Thiele

TEL (478) 552 – 3951
FAX (478) 552 – 4131

KAOCAL

Typical Properties Sheet

G. E. Brightness

Dry, % Minimum	92.5
Slurry, % Minimum	92.0

Particle Size

Finer than 2 Microns, %	83 - 92
-------------------------	---------

Screen Residue Retained

325 Mesh, % Maximum	.010
---------------------	------

pH

Slurry as shipped	7.0 - 8.0
Dry @ 20% Solids	4.0 - 6.0

Slurry

Solids, %	50.0 - 52.0
-----------	-------------

KAOCAL is a Middle Georgia High Brightness Calcined Clay.

Sales are made with the understanding that purchasers will determine the suitability of products for their particular purposes and Thiele makes no warranty for a particular purpose. No warranty of merchantability, nor other warranty, express or implied, is made. Similarly, Thiele Kaolin Company cannot assume responsibility for risks or liabilities, direct, indirect, or consequential, which may result from the use of its products. Likewise, no liability is assumed for any claimed patent infringement occurring by reason of any method of use of the customer.