

TEL (478) 552 – 3951  
FAX (478) 552 – 4131

## **KAOFINE 90**

### **Typical Properties**

#### **G. E. Brightness**

% 90.0 - 92.0

#### **Particle Size**

Finer than 2 Microns, % 96 - 100

#### **Brookfield Viscosity**

No. 2 Spindle, 20 rpm  
Typical @ 70% Solids, cP 600

#### **Screen Residue Retained**

325 Mesh, % Maximum .010

#### **pH**

Slurry as Shipped 6.5 - 7.5  
Spray Dried @ 20% Solids 6.5 - 8.0

#### **Moisture**

Spay Dried, Bulk and Bags, % Maximum 1.5  
Slurry, % Solids 69.0 - 71.0

**KAOFINE 90 is a NO. 1 Fine East Georgia High Brightness Coating Clay.**

Sales are made with the understanding that purchasers will determine the suitability of products for their particular purposes and Thiele makes no warranty for a particular purpose. No warranty of merchantability, nor other warranty, express or implied, is made. Similarly, Thiele Kaolin Company cannot assume responsibility for risks or liabilities, direct, indirect, or consequential, which may result from the use of its products. Likewise, no liability is assumed for any claimed patent infringement occurring by reason of any method of use of the customer.