

TEL (478) 552 – 3951
FAX (478) 552 – 4131

KAOWHITE S

Typical Properties

G. E. Brightness

% 88.0 - 90.0

Particle Size

Finer than 2 Microns, % Minimum 83

Brookfield Viscosity

No. 3 Spindle, 20 rpm
Typical @ 67.5% Solids, cP 450

Screen Residue Retained

325 Mesh, % Maximum .010

pH

Slurry as Shipped or
Spray Dried @ 20% Solids 6.5 - 7.5

Moisture

Spray Dried, Bulk, % 5.0 - 7.0
Slurry*, % Solids 67.0 - 68.0

KAOWHITE S is a Delaminated Middle Georgia Coating Clay.

Sales are made with the understanding that purchasers will determine the suitability of products for their particular purposes and Thiele makes no warranty for a particular purpose. No warranty of merchantability, nor other warranty, express or implied, is made. Similarly, Thiele Kaolin Company cannot assume responsibility for risks or liabilities, direct, indirect, or consequential, which may result from the use of its products. Likewise, no liability is assumed for any claimed patent infringement occurring by reason of any method of use of the customer.