

TEL (478) 552 – 3951  
FAX (478) 552 – 4131

## KAOPRINT

### Typical Properties

<b>G. E. Brightness</b> %	90.0 - 92.5
<b>Particle Size</b> Finer than 2 Microns, %	89 - 94
<b>Brookfield Viscosity</b> No. 2 Spindle, 20 rpm As shipped, Typical, cP	500
<b>Screen Residue Retained</b> 325 Mesh, % Maximum	0.01
<b>pH</b> Slurry as Shipped Spray Dried @ 20% Solids	6.0 - 8.0
<b>Moisture</b> Slurry, % Solids	68.0 - 69.0

Sales are made with the understanding that purchasers will determine the suitability of products for their particular purposes and Thiele makes no warranty for a particular purpose. No warranty of merchantability, nor other warranty, express or implied, is made. Similarly, Thiele Kaolin Company cannot assume responsibility for risks or liabilities, direct, indirect, or consequential, which may result from the use of its products. Likewise, no liability is assumed for any claimed patent infringement occurring by reason of any method of use of the customer.