

Thiele Kaolin Company
P.O. Box 1056
Sandersville, GA 31082

TEL (478) 552 - 3951
FAX (478) 552 - 4131

LOPAQUE M

Typical Properties

G. E. Brightness	
%	76.0 - 82.0
Particle Size	
Finer than 2 Microns, %	88.0 - 96.0
Brookfield Viscosity	
No. 1 Spindle, 20 rpm, cP	200
Typical @ 70.0% Solids	
Screen Residue Retained	
325 Mesh, % Maximum	.010
pH	
Slurry as Shipped	6.5 - 7.5
Spray Dried @ 20% Solids	6.5 - 8.0
Moisture	
Spray Dried, Bulk and Bags, % Maximum	1.5
Slurry, % Solids	69.0 - 71.0

Sales are made with the understanding that purchasers will determine the suitability of products for their particular purposes and Thiele makes no warranty for a particular purpose. No warranty of merchantability, nor other warranty, express or implied, is made. Similarly, Thiele Kaolin Company cannot assume responsibility for risks or liabilities, direct, indirect, or consequential, which may result from the use of its products. Likewise, no liability is assumed for any claimed patent infringement occurring by reason of any method of use of a customer.