

## PRODUCT SPECIFICATION SHEET

### Opamax 16

DRY & SLURRY	
GE Brightness	
Dry, % Minimum	92.5
Slurry, % Minimum	92.0
Particle Size	
Finer than 2 Microns, %, Typical	86.0
Median (D <sub>50</sub> ) diameter, Microns, Typical	0.8
Screen Residue Retained	
325 Mesh, % Maximum	0.0100
pH	
Dry @ 20% solids	4.0 - 6.0
Slurry as shipped	6.0 - 8.0
Moisture	
Dry, Bulk & Bags, % Maximum	1.5
Slurry, % solids	49.0 - 52.0

**DISCLAIMER:** Sales are made with the understanding that purchasers will determine the suitability of products for their particular purposes. THIELE DISCLAIMS ANY AND ALL EXPRESS OR IMPLIED WARRANTIES, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Thiele does not assume responsibility for risks or liabilities, direct or indirect, which may result from use of its products. Thiele also does not assume liability for any actual or claimed patent infringement, safety violation or breach of contract based on use of its products.

*Unless signed by authorized Personnel, this document is provided as reference to a controlled document.*